



# #80 Premium Acrylic Coating

## DATA SHEET

### FOR PROFESSIONAL USE ONLY

**COMPLIANCE:** Miami-Dade County Product Control Approved.  
**DESCRIPTION:** Use TopShield PRO #80 Premium Acrylic Coating to protect the roof, resist mildew and reflect UV rays and blistering heat. TopShield PRO #80 white acrylic flexes with the roof's movement to resist cracking and peeling while reducing roof surface temperatures.

**PREPARATION:** All surfaces must be dry and free of dust, dirt, oil, loose granules, gravel, peeling paint and all other foreign matter. Rusty metal must be cleaned with a wire brush and primed with metal primer before application of this product. Surfaces with mildew growth or stains must be cleaned with a bleach solution (2 parts water to one part bleach) prior to applying this product. Rinse thoroughly. Pressure washing entire surface is recommended for best results (use only a wide fan tip - do not allow stream to tear into roof surface). Repair all leaks and cracks with Polyester Reinforcing Fabric and a white roof patch. Allow to cure 24 - 36 hours before application of roof coating. Surfaces previously coated with aluminum, asphalt or tar should be allowed to cure for a minimum of one summer season prior to coating with this product. Do not heat or thin. **DO NOT APPLY WHEN RAIN OR HEAVY DEW IS EXPECTED WITHIN 24 HOURS OF APPLICATION COMPLETION.**

**FOR BEST RESULTS:** Apply a coat of Emulsion. Embed a polyester reinforcing mat.

**APPLICATION:** For exterior use only. Protective clothing, gloves, and eyewear should be used during application of this product. Always apply on a clear, warm sunny day. Apply in morning hours to allow maximum cure time. Temperatures must be above 50 °F (for 24 hours) and rising, but not above 110 °F. Drying conditions are rated at a maximum relative humidity of 50%. Apply with a 3/4" nap exterior paint roller or professional airless sprayer. First, apply one coat over all seams and joints. Allow to cure for one hour or until dry, then apply two (2) uniform coats over entire surface, avoiding excessive rolling. Two full coats are needed for all applications. Dries for recoat in 4 hours and fully cures in 24 - 36 hours at 70 °F & 50% relative humidity. Higher humidity, thicker films, poor air flow and lower temperatures will increase dry times. **DO NOT APPLY TO FLAT SURFACES, POOR DRAINAGE AREAS, OR WHERE PONDING WATER WILL EXIST.** Keep closed when not in use. Not for use on EPDM or some single ply membranes. Seal container when not in use.

**COVERAGE RATE:** 1 1/2 gallons per square, per coat. Two coats are required for a total application of 3 gallons per square.

**SPRAY INFO:** 2000-3000 PSI, .030 - .041 Tip Size, 1-3 GPM.

**NOTE:** If roof becomes hot (over 100 °F) during application, lightly mist roof surface with water spray to prevent coating from drying too fast. Remove any excess or puddling water prior to coating. If roof surfaces become soiled as they age, due to the elements, elastomeric can be cleaned with a mild water and bleach solution. Excessive scrubbing should be avoided.

**STORAGE & HANDLING PRECAUTIONS:** Do not allow product to freeze. Protective clothing, gloves, and eyewear should be used during application of these products. When transporting this product, ensure that lid is tight and pail secure and upright. Do not allow pail to tumble as this may cause lid to loosen and leakage to occur. Do not transport on passenger seats or inside the passenger compartment of any vehicle. Store product in the cargo area of vehicle, and secure over protective cloths to prevent damage due to accidental spills. Close container after use.

**CLEAN-UP:** Clean tools with soap and water.

©2021 TopShield® PRO

Manufactured For:  
 SRS Distribution, Inc.  
 7440 S. Hwy 121  
 McKinney, TX 75070

See SDS for more information

### TYPICAL PHYSICAL & PERFORMANCE CHARACTERISTICS:

Weight Per Gallon	12 lbs.
Solids by Weight*	65%
Solids by Volume*	51%
Viscosity (ASTM D562)	110-140 ku
Elongation (ASTM D2370)	275%
Tensile Strength (ASTM D2370)	250 psi.
Elongation, post weathering (%)	125%
Reflectivity (ASTM C1549)	.87 (Initial) .74 (3 year)
Emissivity	.89 (Initial) .90 (3 year)
SRI Value	110 (Initial) 92 (3 year)
Permeability (ASTM D1653)	<15 perms
Adhesion to Polyurethane Foam	>3.0 lbs./in.
Consistency	Brush, Roller or Spray
Skin Time (50% Relative Humidity, 70 °F)	4 hours
Full Cure (50% Relative Humidity, 70 °F)	24 - 36 hours
Application Temperatures	55 °F & Rising
Flammability	N/A (water based)
Clean-up Tools	Warm Water & Soap

\*Specification data may vary +/- 5% from published values.

### Approx. Shipping Weights: (Note: All approx. weights include container)

5 gallons (18.9L)	63 lbs.
55 gallon drum (208.2L)	704 lbs.

**VOC: <50 g/L (regulatory)**

**WARRANTY AND DISCLAIMER:** SRS Distribution, Inc. (herein SRS) hereby warrants to the original purchaser, contingent upon original proof of purchase, that this product will be free from any and all manufacturing defects that may materially and adversely affect the product's performance at the time the product is manufactured. Should a manufacturing defect materially and adversely affect this product's performance, SRS shall, within its sole discretion and upon receipt of Purchaser's timely written notice within the Warranty Period, provide replacement product(s) or refund the purchase price of the defective product. **THIS LIMITED WARRANTY IS PURCHASER'S SOLE AND EXCLUSIVE WARRANTY AND REPLACES ALL OTHER WARRANTIES, CONDITIONS, REPRESENTATIONS AND GUARANTEES, WHETHER EXPRESS OR IMPLIED, WHETHER BY STATUTE, AT LAW OR IN EQUITY, INCLUDING THE IMPLIED WARRANTIES OF MERCHANTABILITY AND FITNESS FOR A PARTICULAR PURPOSE.** This limited warranty does not cover labor or installation costs, leaks, or materials not manufactured by OEM supplier, consequential damages or incidental damages. Some states do not allow limitations on how long an implied warranty lasts, so the above limitation may not apply to you. This warranty gives you specific legal rights, and you may also have other rights which vary from state to state. Direct all warranty claims in writing along with original proof of purchase to TopShield PRO, c/o Warranty Claims Department, 7440 State Highway 121, McKinney, TX 75070-2196. The exclusive venue for any legal action arising out of the purchase of this product or this warranty shall be had in a court of competent jurisdiction within Hillsborough County, Florida. Florida law shall govern. For additional Standard Limited Warranty information contact SRS at (855) 569-1550 or at info@srstopshield.com.

